




ZINC US-MIL-A-18001k ALLOY SPECIFICATION

Components:

Al 0,1-0,5% range
Fe 0,005% max
Pb 0,006% max
Cd 0,025-0,07% Max
Cu 0,005% max
Zn remaining

Capacity: 780 Ah/kg

Efficiency: 95%

Potential: - 1110 mV Cu -

CuSO₄ electrolyte artificial sea water DIN 50905

Insert quality: Plate, bar section EN10025 Grade S235/S275

Insert welding: All fabrication of steel inserts are according EN10287 and EN10288

NET WEIGHT: 13,3 kg
GROSS WEIGHT: 15,0 kg
INSERT WEIGHT: 1,7 kg

Company address:
Tijnstraat 109
2984AN Ridderkerk
The Netherlands
Tel. +31 (0) 180 420 055
Fax. +31 (0) 180 499 810
E-mail. info@nedmarine.com
www.nedmarine.com



Drawing name:

NED 150Z

Drawing No.:
17.0180

Rev:
0

Sheet:
1/1

Drawn:
R.D.

Approved:
G.M.

Scale:
-

Date:
06/06/2017

Ned T.D. 16 003